

6. Result

- The Vee Bee Degree of concrete second(s) indicate Low/ Medium/ High Degree of workability

Work Description	Workability Measurement		Vee-Bee time (seconds)
	Slump (mm)	Compaction Factor	
Moist earth	-	-	40 to 25-20
Very Dry	-	0.70	20 to 15-10
Dry	0 - 25	0.75	10 to 7-5
Plastic	25 - 50	0.85	5 to 4-3
Semi Fluid	75 - 100	0.90	3 to 2-1
Fluid	150 - 175	0.95	More Fluid than 1

Table 1 : Workability of Concrete based on Vee-Bee Test

7. Video

- [Vee-Bee Test on Concrete](#)